

Polypropylene – Stock Shapes

Chemical designation

PP

Colour

Natural/Black

Density

0.91 g/cm³

Fillers

Mechanical properties	parameter	value	unit	norm	comment
Modulus of elasticity (tensile test)		1350	MPa	DIN 53457	
Tensile strength at yield		32	MPa	DIN EN ISO 527	
Elongation at break		13	%	DIN 53455	
Notched impact strength (Charpy)		7	kJ/m ²	DIN EN ISO 179	
Ball indentation hardness		70	MPa	DIN EN ISO 2039-1	
Thermal properties	parameter	value	unit	norm	comment
Service temperature	long term	100	°C		
Thermal expansion (CLTE)	23-60°C, long.	16	10 ⁻⁵ *K ⁻¹	ISO 11359-2	
Thermal conductivity		0.22	W/(K*m)	DIN 52612	
Electrical properties	parameter	value	unit	norm	comment
Surface resistance		10 ¹³	Ω	DIN 53482	
Dielectric strength		>55	kV/mm	DIN 53481	
Other properties	parameter	value	unit	norm	comment
Water absorption	saturation (23°C)	0.1	%	DIN 53495	
Flammability		HB		UL94	

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes.